


Crack Treatment

Detail No.: DC-1-A

Date: September 2007



Notes:

- 1] Saw cut cracks greater than 1/16" wide. Blow dust out of saw cut. Apply CR674 StoPur Urethane Primer. Install backer rod and fill with urethane sealant. Allow sealant to cure overnight. If crack is non-moving saw cut should be 1/4" by 1/4" omit backer rod.
- 2] Apply CR675 StoPur deck base coat over hair line cracks, cold joints, and sealed cracks.
- 3] Apply CR675 StoPur deck base coat per instructions.
- 4] Apply CR679 StoPur decorative top coat per instructions.

ATTENTION

Sto products are intended for use by qualified professional contractors, not consumers, as a component of a larger construction assembly as specified by a qualified design professional, general contractor or builder. They should be installed in accordance with those specifications and Sto's instructions. Sto Corp. disclaims all, and assumes no, liability for on-site inspections, for its products applied improperly, or by unqualified persons or entities, or as part of an improperly designed or constructed building, for the nonperformance of adjacent building components or assemblies, or for other construction activities beyond Sto's control. Improper use of Sto products or use as part of an improperly designed or constructed larger assembly or building may result in serious damage to Sto products, and to the structure of the building or its components. **STO CORP. DISCLAIMS ALL WARRANTIES EXPRESS OR IMPLIED EXCEPT FOR EXPLICIT LIMITED WRITTEN WARRANTIES ISSUED TO AND ACCEPTED BY BUILDING OWNERS IN ACCORDANCE WITH STO'S WARRANTY PROGRAMS WHICH ARE SUBJECT TO CHANGE FROM TIME TO TIME.** For the fullest, most current information on proper application, clean-up, mixing and other specifications and warranties, cautions and disclaimers, please refer to the Sto Corp. website, www.stocorp.com.

www.stocorp.com